

SK-32

- AL2O3 : 30-32%
- FE2O3 : 2.5%
- A.P : 24-25%
- B.D : 1.9-2.0 gm/cc
- C.C.S : 300 kgs/cm²
- RUL : 1250-1300



L.L.D 鋁業貿易有限公司